



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01J 13/00	A1	(11) International Publication Number: WO 99/32218 (43) International Publication Date: 1 July 1999 (01.07.99)
(21) International Application Number: PCT/EP98/08244 (22) International Filing Date: 16 December 1998 (16.12.98) (30) Priority Data: 197 56 633.2 19 December 1997 (19.12.97) DE (71) Applicant (for all designated States except US): CABOT CORPORATION [US/US]; 75 State Street, Boston, MA 02109-1806 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): HARTEL, Johannes [DE/DE]; Hasselstrasse 39, D-65812 Bad Soden (DE). FORBERT, Rainald [DE/DE]; Harzweg 1, D-65439 Flörsheim (DE). (74) Agents: MAI, Peter et al.; John-F.-Kennedy-Strasse 4, D-65189 Wiesbaden (DE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: A METHOD FOR THE SUB-CRITICAL DRYING OF LYOGELS TO PRODUCE AEROGELS		
(57) Abstract <p>The present invention refers to a method for the sub-critical drying of lyogels to produce aerogels. The method for the sub-critical drying of lyogels to produce aerogels provides for the lyogel particles to be disposed as a fixed bed and for a drying gas to be passed through them.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Description

A method for the sub-critical drying of lyogels to produce aerogels

The invention relates to a method for the sub-critical drying of lyogels to produce aerogels.

Lyogels are gels which contain a liquid, the dispersing agent. In the particular instance where the gel fluid is water, they are also referred to as hydrogels. In the present Application, the term 'lyogel' also includes hydrogels. Aerogels in the wider sense, i.e. in the sense of "gel with air as the dispersant", a suitable gel is produced by drying. The term "aerogels" in this sense includes aerogels in the narrower sense, xerogels and cryogels. In this respect, a dried gel is referred to as an aerogel in the narrower sense if the fluid of the gel is eliminated at temperatures above the critical temperature and starting from pressures which are above the critical pressure. On the other hand, if the fluid of the gel is removed sub-critically, for example with the formation of a fluid-vapour interface, then the resulting gel is also frequently referred to as a xerogel.

Where the use of the term aerogels in the present Application is concerned, there are gels which are sub-critically dried.

Aerogels have a very low density and high porosity for solid substances. Therefore, and on account of the minimal pore size, aerogels, particularly those with porosities of over 60% and densities below 0.6 g/cu.cm, display an extremely low thermal conductivity and are therefore used as heat insulating materials such as are described for instance in EP-A 0 171 722.

For industrial applications, aerogels are predominantly used as granulate. For the application, it is in this respect essential for the aerogel granulate to be used to consist of particles of a suitable form, preferably spherical form, and size distribution.

By virtue of their low density, however, aerogels also exhibit low mechanical stability, particularly in respect of sheer loadings and against abrasion.

By reason of the capillary forces which occur in sub-critical drying and the shrinkage involved, not all lyogels are suitable for sub-critical drying to produce an aerogel. During drying, the gel shrinks considerably if the meniscus of the fluid migrates into the interior of the gel, in order, with effect from a certain point in the drying process, to spring back more or less completely into its starting form again. Consequently, depending upon the qualities of the inner gel surface, a certain minimum stability of the gel network is essential, modification of the inner gel surface often being required in order to prevent a reaction by adjacent pore walls in the shrunk condition and a collapse of the gel which this would entail.

Corresponding processes in which the inner surface of an SiO_2 lyogel is organically modified and the resulting gel is sub-critically dried to produce an aerogel, are disclosed for example in US-A-5 565 142, DE-A-43 42 548 and in the unpublished German Patent Application 19648798.

Gels which are unsuitable for sub-critical drying collapse under sub-critical drying, with a loss of the porous structure and therefore they no longer display the favourable properties of aerogels.

According to the gel, surface modification, granular form and size and drying conditions, so gel particles can, during drying, be destroyed on a macroscopic scale, i.e. while retaining the nanoporous structure. It is true that the aerogel retains its properties but on account of the now smaller granular size an irregular or undefined grain shape, it can no longer be used so satisfactorily.

Drying methods which at first sight appear obvious for such drying problems are not readily suited to major industrial production of aerogel granulate of a definite form.

By reason of the low density of the aerogels, a fluid bed drying system has been found to be unsuited to major industrial production. In order not to carry the aerogel particles out of the layer, it would be necessary to work below the fluidising point; the necessary gas flow velocities would then be so low that there would be no guarantee of heat being supplied and vapour dispersed in an acceptable time for drying. Were greater gas flow velocities to be used, then the aerogel would not be completely dried since it will be conveyed out of the dryer. Furthermore, in the fluidised phase, gel particles collide with one another so that there is considerable abrasion and grain fracture.

Contact drying proves to be not sufficiently effective since due to the high heat insulating capacity of the aerogels, a transfer of heat into layers more remote from the contact surface does not take place quickly enough so that only minimal layer thicknesses and therefore, in view of the quantities needed, excessively great surface areas would be needed.

In accordance with DE-A-43 16 540, aerogels are dried by dielectric processes. Due to the necessary electrical energy and the relatively high investment for an appropriate drying apparatus, however, these methods are not sufficiently economical.

Therefore, the object of the present invention was to provide a method for the sub-critical drying of lyogels which are suitable for sub-critical drying to produce aerogels and which minimises the destruction of aerogel particles and the abrasion of aerogel particles during drying and which can be used on a large industrial scale.

Surprisingly, the problem is resolved by a method for the sub-critical drying of lyogels to produce aerogels and which is characterised in that the lyogel particles are disposed as a static bed and have a dry gas flowing through them.

Carried out in this way, the drying does not lead to grain fracture or abrasion since the particles are stationary in their bulk. Surprisingly, the drying can be carried out in relatively short times and in layer heights which are considerable for fixed bed drying.

In principle, any lyogels which can be dried sub-critically are suitable for the method, i.e. their gel structure must be sufficiently stable to withstand collapse of the framework by the action of capillary forces and are if necessary suitably surface modified in order for example to prevent a reaction between pore walls in the shrunken condition.

Where the lyogels are concerned, these may according to the type of gel structure be organic or inorganic lyogels. For example, they can be produced on a basis of metal oxides which are suitable for the Sol-gel technique (G. J. Brinker, G. W. Scherer, Sol-Gel Science 1990, chapters 2 and 3), such as for example Si- or Al-compounds or on the basis of organic substances which are suitable for the sol-gel technique such as for example melamine formaldehyde condensates (US-A-5 086 085) or resorcin formaldehyde condensates (US-A-4 873 218) or even on the basis of mixtures of the above-mentioned materials. Preferably, they are SiO_2 gels and particularly preferably organically surface modified SiO_2 gels such as are described for example in the unpublished German Patent Application No. 19648798.

Where the gel fluid is concerned, this may in principle be pure substances or mixtures, the gel fluid preferably containing more than 50% by weight of organic solvents, preferably acetone or hexamethyl disiloxane. Naturally, the gel fluid may also contain small quantities of other substances such as for example hydrochloric acid or residues of water.

The lyogel particles can in principle be of any desired form and size but preferably substantially spherical particles with diameters between 100 μm and 5 cm and particularly preferred are those with diameters between 0.5 mm and 5 mm. It is also possible to dry mixtures of particles of different shape and/or different size.

In order to avoid already dried and therefore lightweight aerogel particles being blown away, it would among other things be necessary for the velocity of the dry gas flow to be low so that no dried aerogel particles are carried away. However, this results in low gas flows and therefore a very limited energy input. For drying aerogels, a rapid energy input is advantageous. For using relatively high drying gas flow velocities, the bulk must therefore, at those places where the gas flow emerges from the fixed bed, be limited by at least one arrangement which is permeable to the drying gas but not to the particles.

Surprisingly, the fixed bed is preferably and in per se known manner, traversed by the drying gas flow passing through it downwards, so that the arrangement which is permeable to the drying gas but not to the particles is constituted by the carrier of the fixed bed. The drying apparatus which is then to be used is consequently not only simpler and less expensive but grain fracture is also reduced, since the upper layers which press down onto those underneath are the first to be dried. The dried and mechanically sensitive aerogels then lie on the heavier and less dried and also mechanically loadable gel particles and are not heavily loaded mechanically.

For a continuous operation, the fixed bed may also be moved with the carrier, e.g. on a suitable belt. Preferably, the gas flow then passes through the fixed bed crosswise to the direction of movement.

The thickness of the fixed bed in the direction of flow of the drying gas stream can be surprisingly great. Preferably, it is between 20 cm and 100 cm and particularly preferably between 20 and 60 cm.

Any gas suitable for drying can be used as the drying gas; if the gel fluid contains large fractions of organic solvents, then possibly an inert gas such as nitrogen should be used. The input gas flow can already contain solvent gas which the process allows, in other words a circulatory pattern of gas flow, whereby, as usual, solvent gas is constantly

eliminated from the circuit, for example by condensation. To accelerate the drying as a whole, it may be advantageous first to dry the gel in a circulatory fashion but to use fresh drying gas for drying the last residues of gel fluid.

The method according to the invention can be carried out by apparatus known to the man skilled in the art, e.g. fixed bed driers, suitable containers with screen bottoms or suitable drying belts, etc., which may possibly be modified in a manner evident to a man of the art.

Preferably, the method for drying surface modified SiO_2 aerogels such as disclosed for example in DE-A-43 42 548 or in the unpublished German Patent Application 196 487 98 will be used.

In this case, if the gel fluid contains more than 50% by weight hexamethyl disiloxane or acetone, then the temperature of the drying gas is preferably between 100°C and 200°C and with particular preference between 140°C and 180°C.

In the case of the said surface modified SiO_2 aerogels, the incident flow velocities are preferably in the range between 1 and 40 cm/s and particularly preferably between 5 and 30 cm/s.

Although the method is particularly suitable for producing aerogels with densities below 300 g/cu.cm, it is also possible to use it for drying xerogels of greater density.

The method according to the invention will be described hereinafter with reference to an example of embodiment but without however being limited thereby.

Example:

A surface modified SiO_2 lyogel which has been produced in accordance with examples 1 to 4 in the unpublished German Patent Application 1964877798 and which has a sharp

grain size distribution around 1 mm diameter is dried in a fixed bed with a height of 50 cm with a stream of nitrogen flowing through the fixed bed from the top downwards at an incident flow velocity of 20 cm/s and with a gas inlet temperature of 160°C. Initially, the gel is dried for 2½ hours in a circulatory manner, the drying gas leaving the fixed bed saturated with moisture and after thorough condensation with a charge of 10g/kg inert gas, it is again introduced into the fixed bed. Afterwards, drying is continued for half-an-hour with fresh drying gas. The dried aerogel displays virtually no grain fracture and hardly any abrasion.

Patent claims

1. A method for the sub-critical drying of lyogels to produce aerogels, characterised in that the lyogel particles are disposed as a fixed bed and have drying as passed through them.
2. A method according to claim 1, characterised in that, at those locations at which the gas flow emerges from the fixed bed, the fixed bed is bounded by at least one arrangement which is permeable to the drying gas but not to the particles.
3. A method according to claim 2, characterised in that the fixed bed lies on the said means and has the flow passing through it from the top downwards.
4. A method according to at least one of claims 1 to 3, characterised in that the lyogel is an organically modified gel the framework of which contains SiO_2 .
5. A method according to claim 4, characterised in that the gel fluid predominantly contains hexamethyl disiloxane.
6. A method according to claim 4, characterised in that the gel fluid predominantly contains acetone.
7. A method according to at least one of claims 4 to 6, characterised in that the temperature of the drying gas at the inlet is between 100°C and 200°C .
8. A method according to 6 or 7, characterised in that the incident flow velocity is between 1 cm/s and 40 cm/s.

9. A method according to at least one of the preceding claims, characterised in that the thickness of the fixed bed is between 20 cm and 100 cm in the direction of flow of the drying gas stream.
10. A method according to at least one of the preceding claims, characterised in that the drying gas follows a circulatory system.
11. A method according to at least one of the preceding claims, characterised in that in a first phase of drying the drying gas is circulated while in a second phase fresh drying gas is used.
12. A method according to at least one of the preceding claims, characterised in that the fixed bed is moved together with the means bounding it, the stream of drying gas being passed through the fixed bed crosswise to the direction of movement.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/08244

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B01J13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	W0 97 32662 A (HOECHST AG) 12 September 1997 see claims 1-11 -----	

☐ Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

27 April 1999

Date of mailing of the international search report

07/05/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Fouquier, J-P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/08244

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9732662 A	12-09-1997	US 5680713 A	28-10-1997
		EP 0885059 A	23-12-1998
<hr/>			

Form PCT/ISA/210 (patent family annex) (July 1992)

INTERNATIONALER RECHERCHENBERICHT

Internationales Aktenzeichen

PCT/EP 98/08244

A. KLASSIFIZIERUNG DES ANMELDUNGSGEGENSTANDES

IPK 6 B01J13/00

Nach der internationalen Patentklassifikation (IPK) oder nach der nationalen Klassifikation und der IPK

B. RECHERCHIERTE GEBIETE

Recherchierter Mindestprüfstoff (Klassifikationssystem und Klassifikationssymbole)

IPK 6 B01J

Recherchierte aber nicht zum Mindestprüfstoff gehörende Veröffentlichungen, soweit diese unter die recherchierten Gebiete fallen

Während der internationalen Recherche konsultierte elektronische Datenbank (Name der Datenbank und evtl. verwendete Suchbegriffe)

C. ALS WESENTLICH ANGESEHENE UNTERLAGEN

Kategorie*	Bezeichnung der Veröffentlichung, soweit erforderlich unter Angabe der in Betracht kommenden Teile	Betr. Anspruch Nr.
A	WO 97 32662 A (HOECHST AG) 12. September 1997 siehe Ansprüche 1-11 -----	



Weitere Veröffentlichungen sind der Fortsetzung von Feld C zu entnehmen



Siehe Anhang Patentfamilie

* Besondere Kategorien von angegebenen Veröffentlichungen :

"A" Veröffentlichung, die den allgemeinen Stand der Technik definiert, aber nicht als besonders bedeutsam anzusehen ist

"E" älteres Dokument, das jedoch erst am oder nach dem internationalen Anmeldedatum veröffentlicht worden ist

"L" Veröffentlichung, die geeignet ist, einen Prioritätsanspruch zweifelhaft erscheinen zu lassen, oder durch die das Veröffentlichungsdatum einer anderen im Recherchenbericht genannten Veröffentlichung belegt werden soll oder die aus einem anderen besonderen Grund angegeben ist (wie ausgeführt)

"O" Veröffentlichung, die sich auf eine mündliche Offenbarung, eine Benutzung, eine Ausstellung oder andere Maßnahmen bezieht

"P" Veröffentlichung, die vor dem internationalen Anmeldedatum, aber nach dem beanspruchten Prioritätsdatum veröffentlicht worden ist

"T" Spätere Veröffentlichung, die nach dem internationalen Anmeldedatum oder dem Prioritätsdatum veröffentlicht worden ist und mit der Anmeldung nicht kollidiert, sondern nur zum Verständnis des der Erfindung zugrundeliegenden Prinzips oder der ihr zugrundeliegenden Theorie angegeben ist

"X" Veröffentlichung von besonderer Bedeutung; die beanspruchte Erfindung kann allein aufgrund dieser Veröffentlichung nicht als neu oder auf erfinderscher Tätigkeit beruhend betrachtet werden

"Y" Veröffentlichung von besonderer Bedeutung; die beanspruchte Erfindung kann nicht als auf erfinderscher Tätigkeit beruhend betrachtet werden, wenn die Veröffentlichung mit einer oder mehreren anderen Veröffentlichungen dieser Kategorie in Verbindung gebracht wird und diese Verbindung für einen Fachmann naheliegend ist

"&" Veröffentlichung, die Mitglied derselben Patentfamilie ist

Datum des Abschlusses der internationalen Recherche

27. April 1999

Absenddatum des internationalen Recherchenberichts

07/05/1999

Name und Postanschrift der Internationalen Recherchenbehörde

Europäisches Patentamt, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Bevollmächtigter Bediensteter

Fouquier, J-P

INTERNATIONALER RECHERCHENBERICHT

Angaben zu Veröffentlichungen, die zur selben Patentfamilie gehören

Internationales Aktenzeichen

PCT/EP 98/08244

Im Recherchenbericht angeführtes Patentdokument	Datum der Veröffentlichung	Mitglied(er) der Patentfamilie	Datum der Veröffentlichung
WO 9732662 A	12-09-1997	US 5680713 A	28-10-1997
		EP 0885059 A	23-12-1998

